

PERFORATED WHITE ONE-WAY PRIVACY (HD)

Inside Application



Description


Micro-perforated one-way vision privacy window film which looks white from the outside and blocks the view into buildings during the daytime. This unique product allows excellent see-through for people inside the building with a black tint effect.

- 


Color
White (outside view)
Black tint (inside view)

- 

Surface type
Micro Perforated

- 


Installation
Inside Window Application

- 

Privacy characteristics
DAY: Excellent (*)
NIGHT: N/A
VIEW OUT: Excellent

- 

On window durability
3 Years+

- 

Storage (72°F, 55% humidity)
2 Years

- 

Environmental standard
REACH compliant

Roll Sizes Available

33ft (length) x 60Inch (width)
 164ft (length) x 60Inch (width)

(*) A low level of privacy will be given if there is more light on the inside than on the outside of the window, e.g. if the inside is illuminated at night.

Technical Specification

Face film	Black on warm white laminated polymeric PVC
Thickness	6.0 mil +/- 0.4 mil
Hole pattern	40% perforated; 0.04" diameter micro holes
Adhesive	Transparent, semi-permanent
Protective release liner	Silicone coated paper
Min appl temp	39°F.

Installation Recommendations

For vertical installation on standard glass. Apply using a dry application method. Glass must be thoroughly cleaned beforehand with soap and water. Rinse and dry glass after cleaning.

Not to be applied to fresh paint or ink, polycarbonate, rubber, plastic moldings and certain PVCs. In case of doubt, please test prior to final application.

This product is not recommended for use around a sharp angle where there is a limited area either side of the angle.

The film must not touch the rubber window molding. Not to be washed within 24 hours of application.

✘ Not recommended for use on glass with coatings such as anti-reflective, self-cleaning and scratch-resistance

Maintenance care

Wash with soapy water. Gently wipe with lint cloth or soft bristled brush to remove grease and dirt. Take particular care not to damage the edges and corners. Wash off suds and leave to dry.

Solar Properties

Data calculated based on film applied to clear glass 0.12" thick.

Visible light transmission	36%
Visible light reflection, exterior	56%
Visible light reflection, interior	6%
UV transmission	28%
Solar energy transmission	33%
Solar energy reflection	51%
Solar energy absorption (total)	16%
Glare reduction (relative %)	60%
g value	0.34
Shading coefficient (SC)	0.40

Contact Information

Contra Vision North America, Inc.
 3330 Cumberland Blvd, Suite 500
 Atlanta
 Unites States
 Tel. +1 770 993 6262
 Email: usasales@contravision.com
 Web: www.contravision.com

This document is intended as a source of information, is given without guarantee, and does not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of the product for their specific intended purpose.